


NSF INTERNATIONAL

° Solo - Blu - Rosso
° Only - Bleu - Red

TUBO IN POLIETILENE ALIMENTARE
POLYETHYLENE HOSES FOR FOOD APPLICATIONS
CERTIFICATO • CERTIFIED

CODICE CODE	Ø mm. OUT. INS.	ROTOLI ROLLS	PRESSIONE ESERCIZIO WORKING PRESSURE	PRESSIONE SCOPPIO BURST PRESSURE
TPA * 04025	4 x 2,5	100	20	55
TPA * 0604	6 x 4	100	20	38
TPA * 0806	8 x 6	100	14	28
TPA * 1007	10 x 7	100	20	36
TPA * 1209	12 x 9	100	12	22
TPA ° 15115	15 x 11,5	100	10	30

° B=BLU/BLUE / R=ROSSO/RED

* N=NEUTRO/NEUTRAL / B=BLU/BLUE / NR=NERO/BLACK



COLORI DISPONIBILI - Neutro - azzurro
AVAILABLE COLOURS - Neutral - light blue

TUBO PA 12 - LINEARI SUPERFLESSIBILI
PA 12 - EXTRAFLEXIBLE LINEAR HOSE

CODICE CODE	Ø mm. OUT. INS.	ROTOLI ROLLS	PRESSIONE ESERCIZIO WORKING PRESSURE	PRESSIONE SCOPPIO BURST PRESSURE
TR * F04027	4 x 2,7	100	20	60
TR * F0604	6 x 4	100	21	62
TR * F0806	8 x 6	100	15	44
TR * F1008	10 x 8	100	11	34
TR * F10065	10 x 6,5	100	22	66
TR * F10075	10 x 7,5	100	13	35
TR * F1209	12 x 9	100	15	44
TR * F1210	12 x 10	100	9	28
TR * F1411	14 x 11	50	12	37
TR * F15125	15 x 12,5	50	10	30

* N=NEUTRO/NEUTRAL / AZ=AZZURRO/ LIGHT BLUE



COLORI DISPONIBILI TRASPARENTI
Neutro - azzurro - rosso - verde
AVAILABLE TRANSPARENT COLOURS
Neutral - light blue - red - green

POLIURETANO SERIE 1198 ANTI U.V.
POLYURETHANE 1198 HOSE ULTRAVIOLET RESISTANT

CODICE CODE	Ø mm. OUT. INS.	ROTOLI ROLLS	PRESSIONE ESERCIZIO WORKING PRESSURE	PRESSIONE SCOPPIO BURST PRESSURE
TPUV * 04025	4 x 2,5	100	8	37
TPUV * 0604	4 x 6	100	6	32
TPUV * 0805	8 x 5	100	8	37
TPUV * 08055	8 x 5,5	100	6	30
TPUV * 10065	10 x 6,5	100	8	34
TPUV * 10075	10 x 7,5	100	6	23
TPUV * 1208	12 x 8	100	8	32
TPUV * 1209	12 x 9	100	6	23

* N=NEUTRO / AZ=AZZURRO / R=ROSSO / V=VERDE


TUBO IN ALLUMINIO RIVESTITO IN POLIETILENE NERO ALTA DENSITA'
ALUMINIUM HOSE COVERED WITH HIGH DENSITY BLACK POLYETHYLENE

CODICE CODE	Ø mm. OUT. INS.	PRESSIONE ESERCIZIO WORKING PRESSURE	ROTOLI ROLLS
TDK0604	6 x 4	17	75
TDK0805	8 x 5	17	75
TDK1007	10 x 7	17	75
TDK1209	12 x 9	15	75
TDK1510	15 x 10	15	75

LE PRESSIONI SONO CALCOLATE AD UNA TEMPERATURA DI 20° C.
THE PRESSURES ARE CALCULATED AT A TEMPERATURE OF 20° C.