

Silicone F



liquid self-levelling neutral cure

The coating and casting compound WEICON Silicone F is liquid, self-levelling, spreadable, solvent-free, neutral-curing, weathering-, ageing-, and temperature-resistant up to +180 °C (+356 °F) and suitable for universal use.

It is especially suitable for elastic adhesive bonds, insulations and waterproofing as well as for sealing and casting (max. 10 mm) technical components. It adheres well to steel, aluminium, glass, ceramic and many other materials.

The product can be used in machine and plant engineering, in plastic processing, in the energy and electronics industry, in shopfitting and trade fair construction and in many other areas of industry.

Technical Data

Composition	1 C.-Polysiloxane (Oxime)
density	1,03 g/cm³
Viscosity adhesive	30.000 mPa•s
Stability/Run-off (ASTM D 222)	liquid
Processing temperature	+5 to +40 °C
Cure type	By humidity
Curing condition	+5 to +40 °C and 30 % to 95 % rel. humidity
Skin-overtime*	15 min.
Curing speed (first 24h)	2 - 3 mm
Shelf life (+5°C to +25°C / +41°F to +77°F)	12 months
Shore A hardness (DIN 5355 / ASTM D 224) ± 5	10
Elongation at break acc. to ISO 37, S3A	600 %
Tensile strength acc. to ISO 37, S3A	1,8 N/mm²
Tension strength value at 100 % (ISO 37, S3A)	0,2 N/mm²
Overpaintable (liquid paint)	No

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Building material category (DIN 412)

B 2

Temperature resistance

-40 to +180 °C

*Measured at 50 % relative air humidity and +23 °C

Surface pre-treatment

The surfaces must be clean and free of grease. Many surface contaminants, e.g. oil, dust and dirt, can be removed with WEICON Surface Cleaner. For heavily soiled metal surfaces, we recommend WEICON Cleaner Spray S; WEICON Sealant and Adhesive Remover is suitable for removing old paint or adhesive residues. Most materials can be bonded well to themselves and among each other. For certain materials or extreme requirements, we recommend the use of an adhesion agent (primer). Detailed information on this subject is contained in the primer selection table. A mechanical surface pre-treatment, e.g. sanding or sand-blasting, can considerably improve the adhesion.

Processing

Processing cartridge

Application methods: Hand cartridge gun for 310 ml cartridges, compressed air gun (we recommend a variation with piston rod), automatic dosing systems.

Processing tube

Squeeze out by hand, close tube again immediately after use, opened tubes should be used up as quickly as possible.

Joining the parts to be bonded

To ensure optimum wetting, the parts must be joined before the first skin has been formed on the adhesive (skin-over time).

Storage

When unopened and stored at room temperature (+23 °C and 50 % rel. humidity), WEICON elastic one-component adhesives and sealants have a shelf life of 12 months.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

13200310 Silicone F 310 ml transparent

Accessories:

13250000	Cartridge Cutter, 310 ml
13250001	Cartridge Gun, 310 ml
13250009	Compressed Air Cartridge Gun, 310 ml